

FORM PTO-150 (Modified)
(REV 11-2000)

U.S. DEPARTMENT OF COMMERCE PATENT AND TRADEMARK OFFICE

ATTORNEY'S DOCKET NUMBER

TRANSMITTAL LETTER TO THE UNITED STATES
DESIGNATED/ELECTED OFFICE (DO/EO/US)
CONCERNING A FILING UNDER 35 U.S.C. 371

WEI0023

U.S. APPLICATION NO. (UNKNOWN, SEE 37 CFR

10/030773

INTERNATIONAL APPLICATION NO.

PCT/EP00/03471

INTERNATIONAL FILING DATE

17 April 2000 (17/04/2000)

PRIORITY DATE CLAIMED

30 April 1999 (30/04/1999)

TITLE OF INVENTION

POLYMER-COATED THIN GLASS FILM SUBSTRATES

APPLICANT(S) FOR DO/EO/US

BURKLE, Roland, et al.

Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:

1. ☒ This is a **FIRST** submission of items concerning a filing under 35 U.S.C. 371.
2. ☐ This is a **SECOND** or **SUBSEQUENT** submission of items concerning a filing under 35 U.S.C. 371.
3. ☒ This is an express request to begin national examination procedures (35 U.S.C. 371(f)). The submission must include items (5), (6), (9) and (24) indicated below.
4. ☒ The US has been elected by the expiration of 19 months from the priority date (Article 31).
5. ☒ A copy of the International Application as filed (35 U.S.C. 371 (c) (2))
 - a. ☒ is attached hereto (required only if not communicated by the International Bureau).
 - b. ☐ has been communicated by the International Bureau.
 - c. ☐ is not required, as the application was filed in the United States Receiving Office (RO/US).
6. ☒ An English language translation of the International Application as filed (35 U.S.C. 371(c)(2)).
 - a. ☒ is attached hereto.
 - b. ☐ has been previously submitted under 35 U.S.C. 154(d)(4).
7. ☐ Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371 (c)(3))
 - a. ☐ are attached hereto (required only if not communicated by the International Bureau).
 - b. ☐ have been communicated by the International Bureau.
 - c. ☐ have not been made; however, the time limit for making such amendments has NOT expired.
 - d. ☐ have not been made and will not be made.
8. ☐ An English language translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371(c)(3)).
9. ☒ An oath or declaration of the inventor(s) (35 U.S.C. 371 (c)(4)).
10. ☐ An English language translation of the annexes to the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371 (c)(5)).
11. ☐ A copy of the International Preliminary Examination Report (PCT/IPEA/409).
12. ☒ A copy of the International Search Report (PCT/ISA/210).

Items 13 to 20 below concern document(s) or information included:

13. ☒ An Information Disclosure Statement under 37 CFR 1.97 and 1.98.
14. ☐ An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included.
15. ☒ A **FIRST** preliminary amendment.
16. ☐ A **SECOND** or **SUBSEQUENT** preliminary amendment.
17. ☐ A substitute specification.
18. ☐ A change of power of attorney and/or address letter.
19. ☐ A computer-readable form of the sequence listing in accordance with PCT Rule 13ter.2 and 35 U.S.C. 1.821 - 1.825.
20. ☐ A second copy of the published international application under 35 U.S.C. 154(d)(4).
21. ☐ A second copy of the English language translation of the international application under 35 U.S.C. 154(d)(4).
22. ☒ Certificate of Mailing by Express Mail
23. ☒ Other items or information:

Check No.

101318

U.S. APPLICATION NO. (IF KNOWN, SEE 37 CFR 1.101)

INTERNATIONAL APPLICATION NO.

ATTORNEY'S DOCKET NUMBER

10/030772

PCT/EP00/03471

WE10023

24. The following fees are submitted:

BASIC NATIONAL FEE (37 CFR 1.492 (a) (1) - (5)) :

- ☐ Neither international preliminary examination fee (37 CFR 1.482) nor international search fee (37 CFR 1.445(a)(2)) paid to USPTO and International Search Report not prepared by the EPO or JPO \$1040.00
- ☒ International preliminary examination fee (37 CFR 1.482) not paid to USPTO but International Search Report prepared by the EPO or JPO \$890.00
- ☐ International preliminary examination fee (37 CFR 1.482) not paid to USPTO but international search fee (37 CFR 1.445(a)(2)) paid to USPTO \$740.00
- ☐ International preliminary examination fee (37 CFR 1.482) paid to USPTO but all claims did not satisfy provisions of PCT Article 33(1)-(4) \$710.00
- ☐ International preliminary examination fee (37 CFR 1.482) paid to USPTO and all claims satisfied provisions of PCT Article 33(1)-(4) \$100.00

ENTER APPROPRIATE BASIC FEE AMOUNT =

\$890.00

Surcharge of \$130.00 for furnishing the oath or declaration later than months from the earliest claimed priority date (37 CFR 1.492 (e)). ☐ 20 ☐ 30

\$0.00

CLAIMS	NUMBER FILED	NUMBER EXTRA	RATE	
Total claims	25 - 20 =	5	x \$18.00	\$90.00
Independent claims	1 - 3 =	0	x \$84.00	\$0.00
Multiple Dependent Claims (check if applicable).			<input type="checkbox"/>	\$0.00

TOTAL OF ABOVE CALCULATIONS = \$980.00☐ Applicant claims small entity status. See 37 CFR 1.27. The fees indicated above are reduced by 1/2.

\$0.00

SUBTOTAL = \$980.00Processing fee of \$130.00 for furnishing the English translation later than months from the earliest claimed priority date (37 CFR 1.492 (f)). ☐ 20 ☐ 30 +

\$0.00

TOTAL NATIONAL FEE = \$980.00Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31) (check if applicable). ☐

\$0.00

TOTAL FEES ENCLOSED = \$980.00

Amount to be refunded	\$
charged	\$

- a. ☒ A check in the amount of \$980.00 to cover the above fees is enclosed.
- b. ☐ Please charge my Deposit Account No. _____ in the amount of _____ to cover the above fees. A duplicate copy of this sheet is enclosed.
- c. ☒ The Commissioner is hereby authorized to charge any additional fees which may be required, or credit any overpayment to Deposit Account No. 02-0385. A duplicate copy of this sheet is enclosed.
- d. ☐ Fees are to be charged to a credit card. **WARNING:** Information on this form may become public. Credit card information should not be included on this form. Provide credit card information and authorization on PTO-2038.

NOTE: Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive 37 CFR 1.137(a) or (b)) must be filed and granted to restore the application to pending status.**SEND ALL CORRESPONDENCE TO:**

John F. Hoffman
BAKER & DANIELS
111 East Wayne Street, Suite 800
Fort Wayne, IN 46802

TX: (219) 424-8000
FAX: (219) 460-1700

SIGNATURE

JOHN F. HOFFMAN

NAME

26,280

REGISTRATION NUMBER

OCTOBER 29, 2001

DATE

10/030773

531 Rec'd PCT

29 OCT 2001

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re Application of)
Roland Bürkle et al.) Group:
Serial No.:)
Filed:) Examiner:
Title: POLYMER-COATED THIN)
GLASS FILM SUBSTRATES)

PRELIMINARY AMENDMENT DELETING MULTIPLE DEPENDENT CLAIMS

Assistant Commissioner of Patents
Washington, DC 20231

Sir:

Prior to calculating the filing fee, please enter the following amendments to the application.

IN THE CLAIMS

In claim 3, line 1, delete "one of the claims 1 to 2" and substitute therefor

--claim 1--.

In claim 4, line 1, delete "any of the claims 1 to 3" and substitute therefor

--claim 1--.

In claim 5, line 1, delete "any of the claims 1 to 4" and substitute therefor

--claim 1--.

In claim 6, line 1, delete "any of the claims 1 to 5" and substitute therefor

--claim 1--.

In claim 7, line 1, delete "any of the claims 1 to 6" and substitute therefor

--claim 1--.

In claim 8, line 1, delete "any of the claims 1 to 7" and substitute therefor

--claim 1--.

In claim 9, line 1, delete "any of the claims 1 to 8" and substitute therefor

--claim 1--.

In claim 10, line 1, delete "any of the claims 1 to 9" and substitute therefor

--claim 1--.

In claim 11, line 1, delete "any of the claims 1 to 10" and substitute therefor

--claim 1--.

In claim 12, line 1, delete "any of the claims 1 to 11" and substitute therefor

--claim 1--.

In claim 13, line 1, delete "any of the claims 1 to 12" and substitute therefor

--claim 1--.

In claim 14, line 1, delete "any of the claims 1 to 13" and substitute therefor

--claim 1--.

In claim 15, line 1, delete "any of the claims 1 to 13" and substitute therefor

--claim 1--.

In claim 17, line 1, delete "or 15".

In claim 18, line 1, delete "any of claims 14 to 17" and substitute therefor

--claim 14--.

In claim 19, line 1, delete "any of claims 14 to 18" and substitute therefor

--claim 14--.

In claim 20, line 1, delete "any of claims 14 to 19" and substitute therefor

--claim 14--.

In claim 21, line 1, delete "any of the claims 14 to 20" and substitute therefor

--claim 14--.

In claim 22, line 1, delete "any of the claims 14 to 21" and substitute therefor

--claim 14--.

In claim 23, line 1, delete "any of the claims 14 to 22" and substitute therefor

--claim 14--.

In claim 24, line 1, delete "any of the claims 14 to 23" and substitute therefor

--claim 14--.

In claim 25, line 1, delete "any of the claims 1 to 13" and substitute therefor

--claim 1--.

Respectfully submitted,

John F. Hoffman
Registration No. 26,280

Attorney for Applicant

JFH/pmp

BAKER & DANIELS
111 East Wayne Street, Suite 800
Fort Wayne, IN 46802

Date: October 29, 2001

1/PRTS

10/030773
531 Rec'd PCT/EP 29 OCT 2001

WO 00/66507

PCT/EP00/03471

Polymer-coated Thin Glass Film Substrates

(0001) The invention relates to a glass-plastic composite film, especially for use in electronic components and devices, such as displays, consisting of a glass film which is between 10 μm and 500 μm thick, and a polymer layer with a thickness between 1 μm and 200 μm applied to at least one of its side faces. Furthermore, it relates to methods for manufacturing said glass-plastic composite film and using the same.

(0002) Flat glass substrates are a suitable substrate material for many applications where transparency, high chemical and thermal resistance and defined chemical and physical properties are important. In particular, these are the areas of application where the methods for thin film and thick film technology are used, such as displays, thin and thick film sensors, solar cells, micro-mechanical components and lithographic masks. In recent times, the demand for new product functionalities and areas of applications has called for ever thinner and ultra-thin substrates that have the known good properties of glass substrates, but also have new properties, in part, such as flexibility. Again, the typical fields of application are electronic applications, such as sensors and membrane elements.

(0003) Especially in displays, for example liquid crystal displays (LCD), the trend is increasingly moving toward a more appealing design and therefore new functionalities are required. In particular, these are ultra-thin and especially light displays, for example for portable pocket devices, flexible displays for devices with a rounded housing form, such as cell phones or round pin-type devices or displays for smart cards or shelf price tags or displays that are based on organic or inorganic light emitting layers, the so-called light emitting organic polymer displays (OLED).

(0004) Generally, this type of display is structured as follows: The core is a cell that houses the liquid crystals or the polymers. It is provided with a front and a rear plate on which electrodes are applied. In most liquid crystal displays the front and rear walls of the cell are both joined by a polarizer. In reflective displays, a reflector plate is provided behind the rear polarizer. In the case of the emitting polymers the counterelectrodes can also be vapor-deposited directly to the polymer before the display is sealed with the rear

plate. In order for the display to function as well as possible it must be ensured, for example, that the liquid crystals are able to align as evenly as possible and that the electrode pairs all have the same distance from each other, if possible, as otherwise distortions or localized intensity fluctuations will occur in the display. One influencing factor is the surface quality of the substrates used for manufacturing the individual components.

(0005) Preferred substrate materials for manufacturing the individual components are glass and plastic. The special advantages of glass are that it is chemically and photo-chemically inert, optically isotropic, temperature-resistant, mechanically stable and it also has a hard surface. However, it has a relatively high density, it is brittle and thus highly susceptible to breaking. Breaking glass in the production process not only causes losses for the manufacturer because of high waste, but also because of the fact that the process has to be stopped every time so as to remove all splinters from the machines.

(0006) Plastics have a lower density and they are elastic and resistant to breaking, but they also have various disadvantages: In the past few years, substrate materials have been developed and manufactured on the basis of high-quality plastic films for manufacturing displays as a replacement for thin glass substrates. All these films require complex special manufacturing processes so as to achieve the required properties. Such complex manufacturing processes make the substrates considerably more expensive. It was also found that in spite of considerable development efforts the water and vapor permeability of such substrate films cannot be adequately reduced. The consequences are that the quality and the lifetime of the LCDs made of such substrate films are highly limited. In the so-called OLEDs the oxygen diffusing through the film will result in oxidizing the organic semiconductor layers and the electrodes consisting of base metals and thus it will also reduce the lifetime of the displays. When plastic is used as a protective layer for the display the susceptibility to scratches will reduce the lifetime.

(0007) Similar to the safety glass industry, attempts are being made to combine the favorable properties of glass with the good properties of plastic: In DE-OS 36 15 277 A1, glass panes are coated with plastic by means of melting on so as to provide protection against splintering. DE-OS 31 27 721 A1 specifies plastic sheets which are coated with glass films as scratch protection where the coating takes place under the effects of

pressure and/or heat, but preferably using an intermediate inserted hot-melt adhesive film.

(0008) Analogous, several examples are known in the field of display technology where the properties of glass and plastic are combined. An approach of providing glass with a protective plastic layer is known from the Korean disclosure of patent KR-A 98-3695. In all probability, the glass is brought to the desired thickness by means of etching and the protective plastic layer then has to close the pores caused by the etching and also serve as protection against breaking.

(0009) The break protecting function primarily consists of preventing the propagation of micro-cracks that already exist. Except for saying that it is a resin from the group of thermosetting plastics the selection of the polymer is not discussed in more detail. Also, it is not disclosed in detail how the protective coat is applied. Assuming a commonly used glass thickness for producing displays at the time of the patent application, which typically was between 0.55 mm and 1.1 mm at that time, and the etched glass surface the glass-plastic composite materials produced thus will not meet the current requirements for display applications.

(0010) With regard to the production of polarizer films, DE-OS 196 06 386 A1 describes an oriented optically active dye film of plastic which is applied for mechanical stabilization to a glass film by means of pressing, melting, preferably adhesion. The adhesive agent provides additional mechanical stabilization for the dye film. The thickness of the glass film ranges between 10 and 200 μm , the thickness of the dye film is between 5 and 60 μm .

(0011) Applying the dye film is not without problems. With pressing, the scrap as a result of breaking glass is very high; melting is a complex process which can have an adverse effect on the properties of the dye film; adhesion has the following disadvantages: The process of bonding films, in this case a polymer film with a glass film, is also called laminating. Lamination generally takes place in that pressure is applied by means of rollers. This causes considerable stress on the glass film, which, especially with very thin films, results in breaking or damaging the glass film, for example scratching the surface.

(0012) At least four separate manufacturing processes are required: manufacturing the thin glass, manufacturing the film, coating with adhesive and the actual laminating process, which results in significant costs. Also, the adhesion and laminating methods have to meet high requirements because the product, especially for display applications, must not contain any air or dust particles. For the selection of the adhesive agents it should be taken into consideration that they generally have a limited temperature and solvent resistance. A homogeneous thickness of the glass laminate cannot be adequately ensured because of fluctuations in the thickness of the ductile adhesive layer.

(0013) The use of polymer films in itself is problematic because when the temperature fluctuates they build up considerable pressure and tensile stresses in the laminate because of their high degree of cross-linking. The thermal coefficients of expansion of plastics are higher by an order of magnitude than those of glass. Furthermore, all polymer films are subject to considerable irreversible shrinking following temperature cycles up to near the glass transition temperature of the plastics, which shrinkage can be higher by up to 1 to 2 orders of magnitude than that of glass and which leads to a permanent warping of the laminates. This effect is frequently inhomogeneous and can be anisotropic in the case of oriented films.

(0014) Furthermore, polymer films usually have a not insignificant optical retardation (double refraction) which is clearly above 20 nm. In displays which utilize the double refraction effect of liquid crystals an optical anisotropy of the film is not acceptable. The lateral double refraction of a film is the result of the difference in the refraction indices parallel and vertical relative to the process direction of the films. The optical retardation of a film having the thickness d is the product of the difference in the refraction indices parallel and vertical relative to the process direction of the films and the film thickness. For LCD applications utilizing the double refraction of the liquid crystal only substrates or substrate films with an optical retardation < 20 nm can be used. Most commercially available drawn films, however, have a multiple of said value. Only a few films are available which are below said value, but they are very expensive because of the more complex manufacturing processes.

(0015) For very thin polymer films the fact should be added that they are very difficult to handle in a lamination process and thus will produce poor yields. They are difficult to laminate without warping which may result in additional stresses and distortions of the laminate. Film laminates with a polymer film thickness $< 25 \mu\text{m}$ are virtually impossible to manufacture economically and for industrial production.

(0016) The Japanese disclosure of patent JP-A 4-235527 specifies a plastic substrate on which a glass film is applied so as to improve the surface quality of the plastic substrate such that an electrically conductive layer for mounting electrodes can be applied. Transparent epoxy resins are the preferred material for the plastic substrate. The substrate thickness can range from $100 \mu\text{m}$ up to 10 mm , depending on the intended use, especially when depending on the size of the area of the display to be produced. The thickness of the glass film ranges between $10 \mu\text{m}$ and $500 \mu\text{m}$. Either the glass film and the plastic substrate are bonded together or the resin is poured on the glass. Bonding will cause the problems mentioned above, which can have an adverse effect on the optical properties and the surface quality of the end product. Also, a substrate thickness $> 100 \mu\text{m}$ has the disadvantage that the flexibility of the glass-plastic composite films is limited.

(0017) For all the above introduced end products it is determined by the end product itself which side is processed further and how it can be processed further. JP-A 4-235527 attempts for the first time to change this in that a glass film is applied to both sides of the plastic substrate. However, at least one process step is required for this, for bonding even at least two additional process steps, plus more material. Therefore, it is considerably more expensive to produce an end product both of whose sides can be further processed.

(0018) A material is known from EP 0 838 723 A that is provided with a layer on a glass carrier. Said material is suitable for lithograph prints and for liquid crystal displays. The material comprises a glass carrier which is thinner than 1.2 mm and which is resistant to tensile stresses of up to and above $5 \times 10^7 \text{ Pa}$. Furthermore, the edges in longitudinal direction are configured semi-circular with a radius of approximately 0.5 times the thickness of the carrier.

(0019) EP 0 272 875 A describes an optical memory card and a method for producing the same where the card consists of plastic and aluminum.

(0020) EP 0 759 565 A describes a method for manufacturing a color filter array element. For this, a colored pattern of pixel cells is applied to a thin carrier which is rigid in the horizontal line. Then, a transparent carrier is laminated onto the side of the carrier or the side of the pixel cells, where first a thin glass pane (127 μm) is coated with polycarbonate by means of spin coating.

(0021) After producing the pixel cells a borosilicate glass plate is laminated to the pixel cells under pressure.

(0022) In EP 0 669 205 A, a transparent glass-plastic composite sheet was described which consists of at least one transparent plastic sheet, at least one glass pane and an adhesion promoting intermediate layer. The glass pane is a glass film having a layer thickness between 30 and 1000 μm . The plastic sheet has a thickness of several mm because the composite sheet is intended to be used as a light, scratch-proof glazing in motor vehicles.

(0023) A glass-plastic composite film comprising a glass film having a thickness from 4 to 200 μm which is coated on one or both surfaces with plastic of a thickness of 2 to 200 μm is described in GB 131 98 46. It is produced either with an adhesive agent or with an adhesion promoter. Alternatively, the plastic can also be applied directly from the liquid phase. The plastics used include polyolefins, PVC, PA, polyvinylidene chloride, cellulose, cellulose acetate, polystyrol or polymer mixes or copolymers of said polymers. Particularly preferred are polyester or polyethylene terephthalate. The glass-plastic composite film specified in GB 131 98 46 is preferably used for film material for drawings or as gas and vacuum impermeable packaging material. Consequently, the optical properties, which are important for the application in the field of electronic components, are not relevant for GB 131 98 46 and are not mentioned in said patent.

(0024) The applications WO 99/21707 and WO 99/21708, which were published later, describe laminates consisting of a glass substrate and at least one carrier which can

consist of transparent plastic. The glass layer has a thickness from 10 to 450 μm , and the plastic layer has a thickness of 500 μm .

(0025) The plastic layer can also be applied to the glass without an adhesive agent by means of vacuum lamination. Also proposed is continuous rolling on. If an adhesive agent is used it should be thermally stable up to 200°C. Especially for vacuum lamination it is important that both the plastic and the glass have a low surface roughness, but this is not further quantified. For the adhesive layer silicones, acrylates and polymers that can be cross-linked with UV light are proposed. An adhesion promoter, such as epoxy silane, can also be applied to the glass if a functional layer has to be applied to the glass. The entire laminate can be coated with a sol-gel, if necessary. Because the laminate is to be used especially for displays the plastic and glass should be selected so as to have a similar refraction index.

(0026) WO 99/21708 describes a method for manufacturing semiconductor devices in that a functional layer is applied to a substrate where the substrate is a laminate consisting of a carrier and a glass layer having a thickness of less than 700 μm . It is substantially a laminate like the one described in WO 99/21707.

(0027) In the subsequently published GB 233 58 84 a component is used as a protective element for optoelectronic or electronic components comprising at least one electrically active organic layer, where the component comprises a glass layer having a thickness of >200 μm and a plastic layer, where the plastic layer has a thickness of > 1 mm, preferably around 200 μm . The disadvantage of GB 233 58 84 is the processing of the active organic functional layer which requires a complicated process. The object of this invention is to provide a film which can be widely used, especially for manufacturing displays as a basis for the production of all components, such as the liquid crystal cell, the cell for housing the light-emitting layer in OLEDs or the electrode layer. It should meet not only the current requirements for film quality but future requirements as well and have the advantageous properties of both glass and plastic. The manufacturing method should be limited to the fewest possible steps and be as uncomplicated as possible.

(0028) The problem is solved by means of a glass-plastic composite film which is characterized in that on a general glass-plastic composite film the polymer layer is applied directly to at least one of the side faces so as to especially avoid the disadvantages of laminating and in that one side face on its surface has a waviness of less than 100 nm and/or a roughness $RT < 30$ nm. It is particularly preferred if the streak is also less than 100 nm. For use in the field of electronic components and devices it is of particular advantage if the optical retardation does not exceed 20 nm. A particularly flexible composite is achieved if the thickness of the applied polymer layer is in the range between 1 μm and 100 μm .

(0029) The problem is also solved by the following two methods:

The first method includes the steps of manufacturing a glass film having a thickness of 10 to 500 μm by means of the down-draw process at a drawing rate of 2 to 12 m/min., pretreating the glass film surface, directly applying a polymer layer of 1 to 200 μm thickness in the liquid phase and cutting the polymer-coated glass film.

(0030) The second method comprises the same steps, where the glass film is cut after it is produced and before pretreating its surface and applying the plastic.

(0031) In contrast with the known laminating methods it is possible with the above methods to produce very thin and homogeneous polymer films on the glass film.

(0032) The glass-plastic composite film of the invention in the case of manufacturing displays is suitable because of its high surface quality both for further processing into a polarizer film and into a carrier plate for electrodes and for the use as an outermost protective sheet. Because of the plastic layer the film is resistant to breaking and lighter at the same time, because of the glass film layer it is scratch-proof, hard, mechanically stable and chemically inert. Depending on whether the glass side or the plastic side is processed further either the plastic side serves as break protection or the glass side serves as scratch protection. Because of the low double refraction the glass-plastic composite film of the invention is suitable especially for use in optoelectronic components and devices. The high surface quality of the composite film is of particular importance for manufacturing liquid crystal cells and luminous displays on the basis of

light-emitting layers because rough surfaces can lead to defects in the display, as rough surfaces can easily lead to an uneven alignment of the liquid crystals in the applied orientation layers. Waviness leads to fluctuations in the layer thickness of the active layer (such as liquid crystals) and thus to an inhomogeneous display.

(0033) The roughness RT is determined in accordance with DIN 4762 Part 1-08.60 and corresponds to the max. distance between the profile top and the profile bottom within a reference path. It should not be confused with the roughness RA which corresponds to the arithmetical mean of all distances and generally is only a fraction of RT.

The roughness describes the short-wave portion of the variation from an ideal flat surface. The waviness (measured according to DIN/ISO 11562 with a cutoff of 0.8 to 8.0 mm and 2CRPC 50 filter) describes the average wavelength portion of the variation from an ideal flat surface. The waviness is determined over a measured distance of 20 mm.

The streak is measured with the same device parameters as the waviness, the measured length for analysis is 2 mm.

(0034) In a particularly preferred embodiment both sides of the glass-plastic composite film have the high surface quality of a waviness of less than 100 nm and a roughness RT of less than 30 nm. With this, the uses of the glass-plastic composite film are even more diversified because it can be further processed equally on either side and also opens up the potential of further processing it on both sides.

(0035) In order to achieve the lightest possible, thinnest possible glass-plastic composite film and above all having the highest surface quality it is indispensable that it does in fact only consist of the polymer and the glass film and that it has no adhesive layer.

(0036) Especially in the area of optoelectronic applications the optical retardation is advantageously < 20 nm, preferably < 15 nm, so as to suppress a distortion of the optical signals through the composite film.

(0037) With regard to reducing the weight and the thickness of displays the glass film layers preferably have thickness of 10 to 400 μm , particularly preferably 10 to 200 μm and especially preferably 10 to 100 μm , and the polymer layer preferably has a thickness

of 2 to 100 μm , particularly preferably 2 to 50 μm , and the optical retardation does not exceed 15 nm.

(0038) Because a large portion of breaking glass in glass films is due to micro-cracks which begin at the edges it is advantageous if at least one edge of the glass-plastic composite film is fully covered by the plastic. This prevents both new cracks from developing and the propagation of existing cracks.

(0039) In order to make the glass-plastic composite film insensitive to punctual stresses, such as thrusts with a pointy object, it was found to be advantageous to select the polymers for the plastic layer such that their modulus of elasticity is $< 5,000 \text{ N/mm}^2$, preferably $< 2,600 \text{ N/mm}^2$, particularly preferably $< 1,500 \text{ N/mm}^2$. The arising tensile stress is distributed by the polymer layer to a larger area and it is substantially reduced.

(0040) The modulus of elasticity of a very thin plastic layer can be determined by measuring the penetration depth of force. For this, a test piece of defined geometry, generally a diamond made pyramidal, is pressed into the surface under an increasing load and subsequently relieved again. The modulus of elasticity is the slope of the load relieving straight line (penetration depth in dependence of the load). The measurements are taken with a so-called pico indenter with which very small impression depths between 10 and 100 nm can be achieved. This is necessary because the substrate begins to affect the measurement when the penetration depth exceeds approx. 10% of the layer thickness.

(0041) It was found to be particularly advantageous to select a polymer for the plastic layer such that the transmission of the glass-plastic composite film is more than 90% of the uncoated glass film and the cloudiness from the polymer coating increases by less than 1% compared to the uncoated glass film.

(0042) In order to have as many options as possible for further processing the glass-plastic composite film and to ensure a long lifetime for the products manufactured on the basis of the glass-plastic composite film the glass-plastic composite film is advantageously continuous temperature-resistant (for several hours) up to 130°C and

short-time temperature-resistant (several minutes) up to 140°C, preferably 180°C, particularly preferably 200°C.

(0043) For the manufacture of LCD and OLED displays glass-plastic composite films were found to be particularly advantageous if they have a surface roughness R_T of < 10 nm, particularly preferably < 3 nm, and a waviness of < 80 nm.

(0044) Preferred materials for obtaining optimal glass-plastic composite films are silicone polymer, sol-gel polymer (such asOrmocere®, Nanocomposite), polycarbonate, polyether sulphone, polyacrylate, polyimide, cycloolefin copolymer or polyarylate for the plastic layer and borosilicate glass, aluminosilicate glass, aluminoborosilicate glass, preferably alkali-free borosilicate for the glass layer.

(0045) In order to produce a glass-plastic composite film the glass film itself has to be produced first. In order to produce a glass film with the required surface quality this should be done using the down-draw process at a drawing rate between 2 and 12 m/min. The surface quality of the glass film is the prerequisite for achieving a corresponding surface quality on the plastic side of the glass-plastic composite film. After producing the glass film it can either be directly processed further, or if the steps of pretreating the glass film surface and applying the polymer layer are spatially separated from the glass film production, it can be cut first, which is preferable for the production of smaller and medium-size quantities.

(0046) The glass film surface is pretreated so as to ensure good adhesion for the polymer layer.

(0047) Directly applying a polymer to the glass film surface without an adhesive agent, and in the liquid phase, achieves that the surface of the polymer layer reflects the surface of the glass film, so to speak, and that it has its excellent surface quality. If producing the glass film, pretreating and coating are planned as a continuous process the polymer-coated glass film is cut now.

(0048) The application in the liquid phase to the rigid glass film also ensures that no distortion orientation develops in the polymer film and therefore the optical retardation of the polymer film and thus the composite film is less than 20 nm.

(0049) If the glass film is cut before coating and if extremely thin polymer layers should be achieved the coating preferably takes place by means of spinning or spray spinning. Coating methods which are also suitable for a continuous process are pouring on, rolling on or spraying. Dipping is preferred for applying the polymer layer on both side faces of the glass film.

(0050) In order to increase the resistance to breaking at least one of the edges of the film should also be coated. In the continuous process the edges parallel with the drawing direction are coated, on cut film pieces all four edges can be coated.

(0051) With regard to the properties of the glass-plastic composite film to be produced it is advantageous to use glass films of 10 to 400 μm , preferably 10 to 200 μm and particularly preferably 10 to 100 μm , and to apply polymer layers of 1 to 200 μm , preferably 2 to 100 μm , and particularly preferably 10 to 85 μm .

In order to increase the adhesion of the polymer layer on the glass film the best results are achieved with a surface treatment by UV irradiating the glass film surface in an ozone-containing atmosphere, by corona treatment or by flaming (?).

(0052) In order to support the hardening of the polymer layer the film should be irradiated with ultraviolet light and/or dried under the influence of heat.

(0053) Glass-plastic composite films with particularly good properties are obtained if the polymer used is either silicone polymer or sol-gel polymer or polycarbonate or polyether sulphone or polyacrylate or polyimide or cycloolefin copolymer or a polyarylate. Furthermore, with this method above all the use of borosilicate glass, preferably alkali-free borosilicate glass, is advantageous for producing the glass film.

(0054) The connection of the glass-plastic composite film of the invention with the production of electronic components and optoelectronic devices, especially on the basis of liquid crystals or light-emitting layers, is to be protected as well.

(0055) The invention will be explained by means of

Fig. 1: profile of the glass-plastic composite film at one of the edges
and

Fig. 2 production line for producing the glass-plastic composite film, and
by means of the following examples.

(0056) Fig. 1 shows a profile of a glass-plastic composite film at one of its edges. On the glass film 1 a polymer film 4 is applied directly to the glass film surface 2. Said polymer film 4 extends beyond the glass edge 3 and thus forms an edge enlargement 5 that fully covers the glass edge 3. In this manner, the edge of the glass-plastic composite film is also protected against jolts and the propagation of micro-cracks on the edge, which cracks may exist in the edge, is prevented.

(0057) Fig. 2 shows a potential production line for producing the glass-plastic composite film. In the glass drawing device 10 the glass film 15 is produced by means of the so-called modified down-draw method in that in a hot forming step the glass film 15 is vertically drawn out of the glass tank 11 and the debiteuse 12 and in that it is reformed, if necessary, in the cooling path 13. By directly connecting the coating path minimal contamination and surface variation of the glass surface are achieved before the subsequent coating, which is particularly favorable for the adhesive power of the polymer layer. With a minimal number of treatment, conveyance and intermediate storage steps surface damage and particle contamination are also reduced to a minimum. In order to compensate for an adjustment in the process rates and possible tolerances a buffer path 16 in the form of a loop is provided following the glass drawing device 10 which achieves that the glass drawing and the coating processes are separated. Because the glass film 15 largely hangs free an unacceptable warping of the glass film 15, which may lead to tearing, and the contamination of the glass surface are prevented.

(0058) In continuing, the glass film 15 is then guided horizontally over conveyor rollers 20 and its tensile stress is controlled via traction rollers 21 so as to ensure a constant conveyance speed and tensile stress and to prevent the glass film 15 from tearing. The

surface to be coated is treated in the surface treatment device 22 by means of UV irradiation in an ozone atmosphere. In order to set the required glass temperature before applying the polymer a tempering unit 23 is provided in front of the coating module 24, which tempering unit preheats the ribbon of glass to a precisely defined, homogeneous temperature. The coating is applied by means of the coating module 24. The polymer 25 flows through the sheet die 26 to the transfer roller 27 and is rolled on by means of the latter to the glass film while applying minimal pressure ($< 1 \text{ kg/cm}^2$). In the first drying path 28 the solvent is caused to evaporate. The evaporated solvent is carried back into the process after a conditioning or cleaning so as to reduce the environmental impact and the consumption. A higher temperature of the glass film 15 causes the solvent to evaporate quickly without forming a dry skin on the surface which would prevent the solvent enclosed in the volume from evaporating. Hardening and drying the polymer layer takes place in the UV irradiation path 30 and in the second drying path 31. At the end of the path is a coiling unit 33 with an intermediate layer uncoiling device 32 from which an intermediate layer is enveloped between the glass-plastic composite film layers. The glass-plastic composite film roll is then brought to the cutting equipment.

(0059) Exemplary Embodiment 1

Production of a glass/polysilicone composite $100 \mu\text{m}/40 \mu\text{m}$ by means of roller coating

(0060) A glass film of borosilicate glass of the glass type D 263 (in-house publication Schott-DESAG) with a thickness of $100 \mu\text{m}$ is used, which is produced by means of the down-draw glass drawing method at a drawing rate of the glass ribbon of 5.5 m/min . The surface of the glass substrate has a waviness of 60 nm , a streak of 45 nm and a roughness RT of 9 nm . The surface of the ribbon of glass is activated by means of a corona treatment. The multimeter metal electrode has a width of 500 mm and the distance between the electrode and the glass surface is 2 mm . The frequency is $30\text{-}50 \text{ kHz}$ (automatic frequency regulation) and the output is 150 W . The two-component silicone polymer film on the basis of polydimethyl siloxane (product name Elastosil of Wacker-Chemie GmbH, mixing ratio of the two silicone components $9:1$) which is applied by means of a roller coating method has a thickness of $40 \mu\text{m}$. The roller diameter is 238 mm and the roller length is 550 mm with an average press-on pressure of 0.5 kg/cm^2 . In a subsequent tempering process the silicone-coated ribbon of glass is hardened at 150°C for 10 min. and subsequently cut. The modulus of elasticity of the

silicone layer is 1100 N/cm² and the surface has a waviness of 50 nm, a streak of 41 nm and a roughness of 20 nm. As a result of the roller coating the lateral edges lying parallel with the rolling direction are coated with the silicone polymer. The optical retardation is 15 nm.

(0061) Exemplary Embodiment 2

Production of a glass/polysilicone composite 50 µm/2 µm by means of a spinning process.

(0062) A glass film of an alkali-free borosilicate glass AF 45 (in-house publication Schott-DESAG) is used with a film thickness of 50 µm, a waviness of 80 nm, a streak of 52 nm and a roughness RT of 4 nm. It is produced by means of the down-draw method at a drawing rate of 10 m/min. The film size is 300 x 200 mm². The glass substrate is cleaned by means of a washing process and subsequently activated on the surface for 5 min. by means of a UV ozone treatment (amalgam low pressure radiator, 500 W) at 184.9 nm so as to generate ozone, at 253.7 nm so as to generate oxygen-centered radicals. By means of a spinning process (rotations 2400 1/min.) the glass film is coated with a one-component silicone elastomer (product name Elastosil) of Wacker-Chemie GmbH (dissolved in hexane at a polymer/hexane ratio of 1:21) and subsequently dried for 15 min. at 120°C in a forced-air oven. The layer thickness is 2 µm. As a result of the spinning coating all four lateral edges are coated with the silicone polymer. The modulus of elasticity of the silicone layer is 500 N/mm² and the surface has a waviness of 67 nm, a streak of 43 nm and a roughness RT of 9 nm. The optical retardation is 5 nm.

(0063) Exemplary Embodiment 3

D 263 glass/polycarbonate composite 145 µm/3 µm by means of a spinning process.

(0064) A glass film of the glass type D 263 (in-house publication Schott-DESAG) is used as glass substrate with a thickness of 145 µm, which is produced by means of the down-draw method at a drawing rate of 4.2 m/min., with a waviness of 28 nm, a streak of 12 nm and a roughness RT of 8 nm. The glass substrate is cleaned by means of a washing process and subsequently activated on the surface for 5 min. by means of a UV ozone treatment (amalgam low pressure radiator, 1000 W) at 184.9 nm so as to generate ozone, at 253.7 nm so as to generate oxygen-centered radicals.

(0065) By means of a spinning process (rotations 1400 1/min.) the glass film is coated with a polycarbonate film (polycarbonate/methylene chloride solution, at a ratio of 1:19) and subsequently dried for 20 min. at 80°C in a forced-air oven. The layer thickness is 3 µm. As a result of the spinning coating all four lateral edges are coated with the polycarbonate film. The modulus of elasticity of the polycarbonate layer is 1350 N/mm² and the surface has a waviness of 30 nm, a streak of 16 nm and a roughness RT of 9 nm. The optical retardation is 9 nm.

(0066) Exemplary Embodiment 4

AF 45 glass/polyether sulphone (PES) 200 µm/85 µm by means of extruding.

(0067) A glass film of an alkali-free borosilicate AF 45 (in-house publication Schott-DESAG) with a film thickness of 200 µm is used. The surface of the glass substrate has a waviness of 55 nm, a streak of 36 nm and a roughness (RT) of 7 nm. The drawing rate of the ribbon of glass is 2.8 m/min.

(0068) The surface of the glass ribbon is activated by means of a corona treatment. The stick electrode has a width of 500 mm and the distance between the electrode and the glass surface is 4.5 mm. The frequency is 30-50 kHz (automatic frequency regulation) and the output is 250 W. The PES film applied by means of an extruding method at a drawing rate of 2.8 m/min. at 380°C has a thickness of 85 µm. The glass-PES composite is cut after a 5-min. cooling period. The modulus of elasticity of the PES layer is 3200 N/mm² and the surface has a waviness of 68 nm, a streak of 49 nm and a roughness RT of 15 nm.

(0069) As a result of the extrusion coating the lateral edges lying parallel with the drawing direction are coated with the PES polymer. The optical retardation is 18 nm.

(0070) Exemplary Embodiment 5

AF 45 glass/polyacrylate composite 50 µm/10 µm by means of spray coating.

(0071) A glass film of an alkali-free borosilicate glass AF 45 (in-house publication Schott-DESAG) is used with a film thickness of 50 µm, a waviness of 80 nm, a streak of

56 nm and a roughness RT of 4 nm. It is produced by means of the down-draw method at a drawing rate of 10 m/min. The film size is 300 x 200 mm². The glass substrate is cleaned by means of a washing process and subsequently activated on the surface for 5 min. by means of a UV ozone treatment (amalgam low pressure radiator, 500 W) at 184.9 nm so as to generate ozone, at 253.7 nm so as to generate oxygen-centered radicals. The 10 µm thick polyacrylate layer is produced by means of a spraying process from an acrylate aerosol, where all four lateral edges are coated with the polymer. The spraying process used is the high pressure low volume (HPLV) method. The 10% polyacrylate solution in N,N-dimethyl ornamide which is preheated to 40° is sprayed via a spray nozzle that has a diameter of 0.6 mm, with an atomizing pressure of 0.55 bar and a feeder pressure for the nozzle of 4 bar. The modulus of elasticity of the acrylate layer is 5000 N/mm² and the surface has a waviness of 75 nm, a streak of 48 nm and a roughness RT of 10 nm. The optical retardation is 8 nm.

(0072) Exemplary Embodiment 6

D 263 glass/cycloolefin copolymer (COC) 145 µm/15 µm by means of extruding.

(0073) A glass film of the glass type D 263 (in-house publication Schott-DESAG) is used as glass substrate with a thickness of 145 µm, which is produced by means of the down-draw method and has a waviness of 28 nm, a streak of 16 nm and a roughness RT of 8 nm.

(0074) The surface of the ribbon of glass is activated by means of a corona treatment. Three successively disposed multimeter metal electrodes are used with a width of 500 mm each and with a distance from the glass surface of 7 mm. The frequency is 30-50 kHz (automatic frequency regulation) and the output per each metal electrode is 120 W. The drawing rate for the glass film is 4.2 m/min. The 15 µm thick COC film is applied by means of an extruding method at 4.2 m/min. at 270°C, where the glass edges parallel with the drawing direction are coated with the polymer. The coated glass ribbon is cut after a cooling period of 7 min. The surface has a waviness of 26 nm, a streak of 14 nm and a roughness RT of 15 nm, the modulus of elasticity is 2800 N/mm². The optical retardation is 10 nm.

(0075) Exemplary Embodiment 7

D 263 glass/polyacrylate composite 145 μm /3.5 μm by means of a dipping method.

(0076) A glass film of the glass type D 263 (in-house publication Schott-DESAG) is used as glass substrate with a thickness of 145 μm , which is produced by means of the down-draw method, with a waviness of 28 nm, a streak of 16 nm and a roughness RT of 8 nm. The size of the glass substrate is 200 x 200 mm². The glass substrate is cleaned by means of a washing process and subsequently activated on the surface for 5 min. by means of a UV ozone treatment (amalgam low pressure radiator, 1000 W) at 184.9 nm so as to generate ozone, at 253.7 nm so as to generate oxygen-centered radicals. The polyarylate is pre-dried in the oven at 130°C, and sodium-dried toluol is used as solvent. The 35 μm thick polyarylate film is applied by means of a dipping method (polyarylate/toluol ratio of 1:18, process temperature 80°C) under nitrogen atmosphere and dried with a subsequent tempering process for 10 min. at 160°.

(0077) All four lateral edges are coated with the 3.5 μm thick polyarylate film. The modulus of elasticity is 2400 N/mm² and the surface has a waviness of 19 nm, a streak of 11 nm and a roughness RT of 10 nm. The optical retardation is 8 nm.

(0078) Exemplary Embodiment 8

D 263 glass/silicone resin composite 100 μm /4.5 μm by means of a spinning process.

(0079) A glass film of the glass type D 263 (in-house publication Schott-DESAG) is used as glass substrate with a thickness of 100 μm , which is produced by means of the down-draw method, with a waviness of 33 nm, a streak of 15 nm and a roughness RT of 6 nm. The size of the glass substrate is 100 x 100 mm². The glass substrate is cleaned by means of a washing process and subsequently activated on the surface for 5 min. by means of a UV ozone treatment (amalgam low pressure radiator, 1000 W) at 184.9 nm so as to generate ozone, at 253.7 nm so as to generate oxygen-centered radicals. The glass film is coated with a methylphenyl silicone resin (product name Silres® of Wacker-Chemie GmbH, silicone resin/xylene solution ratio of 1:3) by means of a spinning method (rotations 5000 1/min.) and subsequently dried for 15 min. at 220°C in a forced-air oven. The layer thickness is 4.5 μm . As a result of the spinning coating all four lateral edges are coated with the silicone resin. The surface has a waviness of 35 nm, a streak of 17 nm and a roughness RT of 9 nm. The optical retardation is 14 nm.

Reference List

- 1 glass film
- 2 glass film surface
- 3 glass edge
- 4 polymer film
- 5 edge enlargement
- 10 glass drawing device
- 11 glass tank
- 12 debiteuse
- 13 cooling path
- 14 rollers
- 15 glass film
- 16 buffer path
- 20 conveyor rollers
- 21 rollers
- 22 surface treatment device
- 23 tempering unit
- 24 coating module
- 25 polymer
- 26 sheet die
- 27 transfer roller
- 28 first drying path
- 29 extraction
- 30 UV irradiation path
- 31 second drying path
- 32 intermediate layer uncoiling device
- 33 coiling unit

Patent Claims

1. Glass-plastic composite film, especially for use in electronic components and devices, for example displays, consisting of a glass film having a thickness between 10 μm and 500 μm , characterized in that a polymer layer having a thickness between 1 μm and 200 μm is applied directly to at least one of its side faces, and in that at least one side on the surface has a waviness of less than 100 nm and a roughness $RT < 30$ nm.
2. Glass-plastic composite film as per claim 1, characterized in that the optical retardation does not exceed 20 nm.
3. Glass-plastic composite film as per one of the claims 1 to 2, characterized in that the streak is less than 100 nm, preferably < 50 nm, particularly preferably < 30 nm.
4. Glass-plastic composite film as per any of the claims 1 to 3, characterized in that both sides on their surface have a waviness of less than 100 nm and a roughness RT of less than 30 nm.
5. Glass-plastic composite film as per any of the claims 1 to 4, characterized in that the glass thickness is 10 to 400 μm , preferably 10 to 200 μm , particularly preferably 10 to 100 μm .
6. Glass-plastic composite film as per any of the claims 1 to 5, characterized in that the thickness of the polymer layer is 2 to 100 μm , preferably 2 to 50 μm .
7. Glass-plastic composite film as per any of the claims 1 to 6, characterized in that the film is also provided with the polymer layer on at least one of its edges.
8. Glass-plastic composite film as per any of the claims 1 to 7, characterized in that the polymer layer has a modulus of elasticity of $< 5,000$ N/mm², preferably $< 2,600$ N/mm², particularly preferably $< 1,500$ N/mm².
9. Glass-plastic composite film as per any of the claims 1 to 8, characterized in that the transmission of the glass-plastic composite film is more than 90% of the uncoated

glass film and that the cloudiness as a result of the polymer coating increases by less than 1%.

10. Glass-plastic composite film as per any of the claims 1 to 9, characterized in that the roughness of the surface RT is < 20 nm, preferably < 10 nm, that the waviness of the surface is < 80 nm, preferably < 50 nm, particularly preferably < 30 nm and that the optical retardation does not exceed 15 nm.

11. Glass-plastic composite film as per any of the claims 1 to 10, characterized in that in continuous use the film is temperature-resistant up to 130°C , and that for short-time heating the film is temperature-resistant up to 140°C , preferably 180°C , particularly preferably 200°C .

12. Glass-plastic composite film as per any of the claims 1 to 11, characterized in that the polymer layer consists of a silicone polymer, a sol-gel polymer, a polycarbonate, a polyether sulphone, a polyacrylate, a polyimide, a cycloolefin copolymer, a polyarylate or a silicone resin.

13. Glass-plastic composite film as per any of the claims 1 to 12, characterized in that the glass film consists of an aluminosilicate glass, aluminoborosilicate glass, borosilicate glass, preferably an alkali-free borosilicate glass.

14. Method for producing a glass-plastic composite film as per any of the claims 1 to 13, comprising the steps:

- producing a glass film having a thickness of 10 to $500\text{ }\mu\text{m}$ using the down-draw process at a drawing rate of 2 to 12 m/min. ;
- pre-treating the glass film surface;
- directly applying a 1 to $200\text{ }\mu\text{m}$ thick polymer layer in the liquid phase;
- cutting the polymer-coated glass film.

15. Method for producing a glass-plastic composite film as per any of the claims 1 to 13, comprising the steps:

- producing a glass film having a thickness of 10 to $500\text{ }\mu\text{m}$ using the down-draw process at a drawing rate of 2 to 12 m/min. ;

cutting the glass film;
 pre-treating the glass film surface;
 directly applying a 1 to 200 μm thick polymer layer in the liquid phase.

16. Method according to claim 15, characterized in that the polymer layer is applied by means of spinning or spray spinning.

17. Method according to claim 14 or 15, characterized in that the polymer layer is applied by means of pouring on or rolling on or spraying or dipping.

18. Method according to any of the claims 14 to 17, characterized in that in addition to the side face at least one edge is coated.

19. Method according to any of the claims 14 to 18, characterized in that a glass film having a thickness of 10 to 400 μm , preferably 10 to 200 μm , particularly preferably 10 to 100 μm is produced in the glass drawing device by means of the down-draw method.

20. Method according to any of the claims 14 to 19, characterized in that the coating produces a polymer layer thickness of 2 to 100 μm , preferably 2 to 50 μm .

21. Method according to any of the claims 14 to 20, characterized in that the surface treatment is performed before the coating with UV irradiation in an ozone-containing atmosphere or with a corona treatment or with flaming (?).

22. Method according to any of the claims 14 to 21, characterized in that subsequent to coating the polymer coating is hardened by means of UV irradiation and/or dried under the influence of heat.

23. Method according to any of the claims 14 to 22, characterized in that the polymer consists of a silicone polymer, a sol-gel polymer, a polycarbonate, a polyether sulphone, a polyacrylate, a polyimide, a cycloolefin copolymer, a polyarylate or a silicone resin.

24. Method according to any of the claims 14 to 23, characterized in that for producing the glass film a glass film of an aluminosilicate glass, aluminoborosilicate glass, a borosilicate glass, preferably an alkali-free borosilicate glass is used.

25. Use of the glass-plastic composite film as per any of the claims 1 to 13 for manufacturing electronic components and optoelectronic devices, especially on the basis of liquid crystals or light-emitting layers.

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65
66
67
68
69
70
71
72
73
74
75
76
77
78
79
80
81
82
83
84
85
86
87
88
89
90
91
92
93
94
95
96
97
98
99
100
101
102
103
104
105
106
107
108
109
110
111
112
113
114
115
116
117
118
119
120
121
122
123
124
125
126
127
128
129
130
131
132
133
134
135
136
137
138
139
140
141
142
143
144
145
146
147
148
149
150
151
152
153
154
155
156
157
158
159
160
161
162
163
164
165
166
167
168
169
170
171
172
173
174
175
176
177
178
179
180
181
182
183
184
185
186
187
188
189
190
191
192
193
194
195
196
197
198
199
200
201
202
203
204
205
206
207
208
209
210
211
212
213
214
215
216
217
218
219
220
221
222
223
224
225
226
227
228
229
230
231
232
233
234
235
236
237
238
239
240
241
242
243
244
245
246
247
248
249
250
251
252
253
254
255
256
257
258
259
260
261
262
263
264
265
266
267
268
269
270
271
272
273
274
275
276
277
278
279
280
281
282
283
284
285
286
287
288
289
290
291
292
293
294
295
296
297
298
299
300
301
302
303
304
305
306
307
308
309
310
311
312
313
314
315
316
317
318
319
320
321
322
323
324
325
326
327
328
329
330
331
332
333
334
335
336
337
338
339
340
341
342
343
344
345
346
347
348
349
350
351
352
353
354
355
356
357
358
359
360
361
362
363
364
365
366
367
368
369
370
371
372
373
374
375
376
377
378
379
380
381
382
383
384
385
386
387
388
389
390
391
392
393
394
395
396
397
398
399
400
401
402
403
404
405
406
407
408
409
410
411
412
413
414
415
416
417
418
419
420
421
422
423
424
425
426
427
428
429
430
431
432
433
434
435
436
437
438
439
440
441
442
443
444
445
446
447
448
449
450
451
452
453
454
455
456
457
458
459
460
461
462
463
464
465
466
467
468
469
470
471
472
473
474
475
476
477
478
479
480
481
482
483
484
485
486
487
488
489
490
491
492
493
494
495
496
497
498
499
500
501
502
503
504
505
506
507
508
509
510
511
512
513
514
515
516
517
518
519
520
521
522
523
524
525
526
527
528
529
530
531
532
533
534
535
536
537
538
539
540
541
542
543
544
545
546
547
548
549
550
551
552
553
554
555
556
557
558
559
560
561
562
563
564
565
566
567
568
569
570
571
572
573
574
575
576
577
578
579
580
581
582
583
584
585
586
587
588
589
590
591
592
593
594
595
596
597
598
599
600
601
602
603
604
605
606
607
608
609
610
611
612
613
614
615
616
617
618
619
620
621
622
623
624
625
626
627
628
629
630
631
632
633
634
635
636
637
638
639
640
641
642
643
644
645
646
647
648
649
650
651
652
653
654
655
656
657
658
659
660
661
662
663
664
665
666
667
668
669
670
671
672
673
674
675
676
677
678
679
680
681
682
683
684
685
686
687
688
689
690
691
692
693
694
695
696
697
698
699
700
701
702
703
704
705
706
707
708
709
710
711
712
713
714
715
716
717
718
719
720
721
722
723
724
725
726
727
728
729
730
731
732
733
734
735
736
737
738
739
740
741
742
743
744
745
746
747
748
749
750
751
752
753
754
755
756
757
758
759
760
761
762
763
764
765
766
767
768
769
770
771
772
773
774
775
776
777
778
779
780
781
782
783
784
785
786
787
788
789
790
791
792
793
794
795
796
797
798
799
800
801
802
803
804
805
806
807
808
809
810
811
812
813
814
815
816
817
818
819
820
821
822
823
824
825
826
827
828
829
830
831
832
833
834
835
836
837
838
839
840
841
842
843
844
845
846
847
848
849
850
851
852
853
854
855
856
857
858
859
860
861
862
863
864
865
866
867
868
869
870
871
872
873
874
875
876
877
878
879
880
881
882
883
884
885
886
887
888
889
890
891
892
893
894
895
896
897
898
899
900
901
902
903
904
905
906
907
908
909
910
911
912
913
914
915
916
917
918
919
920
921
922
923
924
925
926
927
928
929
930
931
932
933
934
935
936
937
938
939
940
941
942
943
944
945
946
947
948
949
950
951
952
953
954
955
956
957
958
959
960
961
962
963
964
965
966
967
968
969
970
971
972
973
974
975
976
977
978
979
980
981
982
983
984
985
986
987
988
989
990
991
992
993
994
995
996
997
998
999
1000
1001
1002
1003
1004
1005
1006
1007
1008
1009
1010
1011
1012
1013
1014
1015
1016
1017
1018
1019
1020
1021
1022
1023
1024
1025
1026
1027
1028
1029
1030
1031
1032
1033
1034
1035
1036
1037
1038
1039
1040
1041
1042
1043
1044
1045
1046
1047
1048
1049
1050
1051
1052
1053
1054
1055
1056
1057
1058
1059
1060
1061
1062
1063
1064
1065
1066
1067
1068
1069
1070
1071
1072
1073
1074
1075
1076
1077
1078
1079
1080
1081
1082
1083
1084
1085
1086
1087
1088
1089
1090
1091
1092
1093
1094
1095
1096
1097
1098
1099
1100
1101
1102
1103
1104
1105
1106
1107
1108
1109
1110
1111
1112
1113
1114
1115
1116
1117
1118
1119
1120
1121
1122
1123
1124
1125
1126
1127
1128
1129
1130
1131
1132
1133
1134
1135
1136
1137
1138
1139
1140
1141
1142
1143
1144
1145
1146
1147
1148
1149
1150
1151
1152
1153
1154
1155
1156
1157
1158
1159
1160
1161
1162
1163
1164
1165
1166
1167
1168
1169
1170
1171
1172
1173
1174
1175
1176
1177
1178
1179
1180
1181
1182
1183
1184
1185
1186
1187
1188
1189
1190
1191
1192
1193
1194
1195
1196
1197
1198
1199
1200
1201
1202
1203
1204
1205
1206
1207
1208
1209
1210
1211
1212
1213
1214
1215
1216
1217
1218
1219
1220
1221
1222
1223
1224
1225
1226
1227
1228
1229
1230
1231
1232
1233
1234
1235
1236
1237
1238
1239
1240
1241
1242
1243
1244
1245
1246
1247
1248
1249
1250
1251
1252
1253
1254
1255
1256
1257
1258
1259
1260
1261
1262
1263
1264
1265
1266
1267
1268
1269
1270
1271
1272
1273
1274
1275
1276
1277
1278
1279
1280
1281
1282
1283
1284
1285
1286
1287
1288
1289
1290
1291
1292
1293
1294
1295
1296
1297
1298
1299
1300
1301
1302
1303
1304
1305
1306
1307
1308
1309
1310
1311
1312
1313
1314
1315
1316
1317
1318
1319
1320
1321
1322
1323
1324
1325
1326
1327
1328
1329
1330
1331
1332
1333
1334
1335
1336
1337
1338
1339
1340
1341
1342
1343
1344
1345
1346
1347
1348
1349
1350
1351
1352
1353
1354
1355
1356
1357
1358
1359
1360
1361
1362
1363
1364
1365
1366
1367
1368
1369
1370
1371
1372
1373
1374
1375
1376
1377
1378
1379
1380
1381
1382
1383
1384
1385
1386
1387
1388
1389
1390
1391
1392
1393
1394
1395
1396
1397
1398
1399
1400
1401
1402
1403
1404
1405
1406
1407
1408
1409
1410
1411
1412
1413
1414
1415
1416
1417
1418
1419
1420
1421
1422
1423
1424
1425
1426
1427
1428
1429
1430
1431
1432
1433
1434
1435
1436
1437
1438
1439
1440
1441
1442
1443
1444
1445
1446
1447
1448
1449
1450
1451
1452
1453
1454
1455
1456
1457
1458
1459
1460
1461
1462
1463
1464
1465
1466
1467
1468
1469
1470
1471
1472
1473
1474
1475
1476
1477
1478
1479
1480
1481
1482
1483
1484
1485
1486
1487
1488
1489
1490
1491
1492
1493
1494
1495
1496
1497
1498
1499
1500
1501
1502
1503
1504
1505
1506
1507
1508
1509
1510
1511
1512
1513
1514
1515
1516
1517
1518
1519
1520
1521
1522
1523
1524
1525
1526
1527
1528
1529
1530
1531
1532
1533
1534
1535
1536
1537
1538
1539
1540
1541
1542
1543
1544
1545
1546
1547
1548
1549
1550
1551
1552
1553
1554
1555
1556
1557
1558
1559
1560
1561
1562
1563
1564
1565
1566
1567
1568
1569
1570
1571
1572
1573
1574
1575
1576
1577
1578
1579
1580
1581
1582
1583
1584
1585
1586
1587
1588
1589
1590
1591
1592
1593
1594
1595
1596
1597
1598
1599
1600
1601
1602
1603
1604
1605
1606
1607
1608
1609
1610
1611
1612
1613
1614
1615
1616
1617
1618
1619
1620
1621
1622
1623
1624
1625
1626
1627
1628
1629
1630
1631
1632
1633
1634
1635
1636
1637
1638
1639
1640
1641
1642
1643
1644
1645
1646
1647
1648
1649
1650
1651
1652
1653
1654
1655
1656
1657
1658
1659
1660
1661
1662
1663
1664
1665
1666
1667
1668
1669
1670
1671
1672
1673
1674
1675
1676
1677
1678
1679
1680
1681
1682
1683
1684
1685
1686
1687
1688
1689
1690
1691
1692
1693
1694
1695
1696
1697
1698
1699
1700
1701
1702
1703
1704
1705
1706
1707
1708
1709
1710
1711
1712
1713
1714
1715
1716
1717
1718
1719
1720
1721
1722
1723
1724
1725
1726
1727
1728
1729
1730
1731
1732
1733
1734
1735
1736
1737
1738
1739
1740
1741
1742
1743
1744
1745
1746
1747
1748
1749
1750
1751
1752
1753
1754
1755
1756
1757
1758
1759
1760
1761
1762
1763
1764
1765
1766
1767
1768
1769
1770
1771
1772
1773
1774
1775
1776
1777
1778
1779
1780
1781
1782
1783
1784
1785
1786
1787
1788
1789
1790
1791
1792
1793
1794
1795
1796
1797
1798
1799
1800
1801
1802
1803
1804
1805
1806
1807
1808
1809
1810
1811
1812
1813
1814
1815
1816
1817
1818
1819
1820
1821
1822
1823
1824
1825
1826
1827
1828
1829
1830
1831
1832
1833
1834
1835
1836
1837
1838
1839
1840
1841
1842
1843
1844
1845
1846
1847
1848
1849
1850
1851
1852
1853
1854
1855
1856
1857
1858
1859
1860
1861
1862
1863
1864
1865
1866
1867
1868
1869
1870
1871
1872
1873
1874
1875
1876
1877
1878
1879
1880
1881
1882
1883
1884
1885
1886
1887
1888
1889
1890
1891
1892
1893
1894
1895
1896
1897
1898
1899
1900
1901
1902
1903
1904
1905
1906
1907
1908
1909
1910
1911
1912
1913
1914
1915
1916
1917
1918
1919
1920
1921
1922
1923
1924
1925
1926
1927
1928
1929
1930
1931
1932
1933
1934
1935
1936
1937
1938
1939
1940
1941
1942
1943
1944
1945
1946
1947
1948
1949
1950
1951
1952
1953
1954
1955
1956
1957
1958
1959
1960
1961
1962
1963
1964
1965
1966
1967
1968
1969
1970
1971
1972
1973
1974
1975
1976
1977
1978
1979
1980
1981
1982
1983
1984
1985
1986
1987
1988
1989
1990
1991
1992
1993
1994
1995
1996
1997
1998
1999
2000
2001
2002
2003
2004
2005
2006
2007
2008
2009
2010
2011
2012
2013
2014
2015
2016
2017
2018
2019
2020
2021
2022
2023
2024
2025
2026
2027
2028
2029
2030
2031
2032
2033
2034
2035
2036
2037
2038
2039
2040
2041
2042
2043
2044
2045
2046
2047
2048
2049
2050
2051
2052
2053
2054
2055
2056
2057
2058
2059
2060
2061
2062
2063
2064
2065
2066
2067
2068
2069
2070
2071
2072
2073
2074
2075
2076
2077
2078
2079
2080
2081
2082
2083
2084
2085
2086
2087
2088
2089
2090
2091
2092
2093
2094
2095
2096
2097
2098
2099
2100
2101
2102
2103
2104
2105
2106
2107
2108
2109
2110
2111
2112
2113
2114
2115
2116
2117
2118
2119
2120
2121
2122
2123
2124
2125
2126
2127
2128
2129
2130
2131
2132
2133
2134
2135
2136
2137
2138
2139
2140
2141
2142
2143
2144
2145
2146
2147
2148
2149
2150
2151
2152
2153
2154
2155
2156
2157
2158
2159
2160
2161
2162
2163
2164
2165
2166
2167
2168
2169
2170
2171
2172
2173
2174
2175
2176
2177
2178
2179
2180
2181
2182
2183
2184
2185
2186
2187
2188
2189
2190
2191
2192
2193
2194
2195
2196
2197
2198
2199
2200
2201
2202
2203
2204
2205
2206
2207
2208



INTERNATIONALE ANMELDUNG VERÖFFENTLICHT NACH DEM VERTRAG ÜBER DIE
INTERNATIONALE ZUSAMMENARBEIT AUF DEM GEBIET DES PATENTWESENS (PCT)

(51) Internationale Patentklassifikation 7 :

C03C 17/32, B32B 17/10

A1

(11) Internationale Veröffentlichungsnummer: WO 00/66507

(43) Internationales

Veröffentlichungsdatum:

9. November 2000 (09.11.00)

(21) Internationales Aktenzeichen: PCT/EP00/03471

(22) Internationales Anmeldedatum: 17. April 2000 (17.04.00)

(30) Prioritätsdaten:

99108440.1

30. April 1999 (30.04.99)

EP

(71) Anmelder (für alle Bestimmungsstaaten ausser AU CA GB IE IL IN JP KE KP LK NZ SG TZ UG US ZA): SCHOTT GLAS [DE/DE]; Hattenbergstrasse 10, D-55122 Mainz (DE).

(71) Anmelder (nur für AE AU BB CA GB GD GH GM IE IL IN KE KP LC LK LR LS MG MN MW NZ SD SG SL SZ TT TZ UG VN ZA ZW): CARL-ZEISS-STIFTUNG Trading as SCHOTT GLAS [DE/DE]; Hattenbergstrasse 10, D-55122 Mainz (DE).

(71) Anmelder (nur für AE BB GD GH GM JP KE LC LR LS MG MN MW SD SL SZ TT TZ ZW): CARL-ZEISS-STIFTUNG [DE/DE]; D-89518 Heidenheim (DE).

(72) Erfinder; und

(75) Erfinder/Anmelder (nur für US): BÜRKLE, Roland [DE/DE]; Am Eselsborn 15, D-55268 Nieder-Olm (DE). DEUTSCHBEIN, Silke [DE/DE]; Wallaustrasse 79, D-55118 Mainz (DE). MAUCH, Reiner [DE/DE];

Kurfalzstrasse 22, D-55218 Ingelheim (DE). SOSSEN-HEIMER, Karl-Heinz [DE/DE]; Auf der Unter 6, D-55263 Wackernheim (DE). WEBER, Andreas [DE/DE]; Max-Planck-Strasse 59, D-55124 Mainz (DE).

(74) Anwalt: WEITZEL & PARTNER; Friedenstrasse 10, D-89522 Heidenheim (DE).

(81) Bestimmungsstaaten: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO Patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), eurasisches Patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), europäisches Patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI Patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

Veröffentlicht

Mit internationalem Recherchenbericht.

Vor Ablauf der für Änderungen der Ansprüche zugelassenen Frist; Veröffentlichung wird wiederholt falls Änderungen eintreffen.

(54) Title: POLYMER-COATED THIN GLASS FILM SUBSTRATES


(54) Bezeichnung: POLYMERBESCHICHTETE DÜNNGLASFOLIENSUBSTRATE



(57) Abstract

The invention relates to a glass-plastic composite film, especially for use in electronic components and devices, such as displays. The inventive film consists of a glass film which is between 10 μm and 500 μm thick, and is characterised in that a polymer layer with a thickness of between 1 μm and 200 μm is applied directly to at least one of the side faces of said film and in that at least one side on the surface of the film has a waviness of less than 100 nm and a roughness $R_t < 30$ nm.

(57) Zusammenfassung

Die Erfindung betrifft eine Glas- Kunststoff- Verbundfolie, insbesondere zur Verwendung in elektronischen Bauteilen und Geräten, beispielsweise Displays, aus einer Glasfolie, die eine Dicke zwischen 10 μm und 500 μm aufweist. Die Erfindung ist dadurch gekennzeichnet, daß unmittelbar auf mindestens einer ihrer Seitenflächen eine Polymerschicht, die eine Dicke zwischen 1 μm und 200 μm aufweist aufgebracht wird und mindestens eine Seite an ihrer Oberfläche eine Welligkeit geringer als 100 nm und eine Rauigkeit $R_t < 30$ nm aufweist.





Declaration and Power of Attorney for Patent Application

Erklärung für Patentanmeldungen mit Vollmacht

German Language Declaration

Als nachstehend benannter Erfinder erkläre ich hiermit an Eides Statt:

daß mein Wohnsitz, meine Postanschrift und meine Staatsangehörigkeit den im nachstehenden nach meinem Namen aufgeführten Angaben entsprechen, daß ich nach bestem Wissen der ursprüngliche, erste und alleinige Erfinder (falls nachstehend nur ein Name angegeben ist) oder ein ursprünglicher, erster und Miterfinder (falls nachstehend mehrere Namen aufgeführt sind) des Gegenstandes bin, für den dieser Antrag gestellt wird und für den ein Patent für die Erfindung mit folgendem Titel beantragt wird:

deren Beschreibung hier beigelegt ist, es sei denn (in diesem Falle zutreffendes bitte ankreuzen), diese Erfindung

☐ wurde angemeldet am _____ unter der US-Anmeldenummer oder unter der Internationalen Anmeldenummer im Rahmen des Vertrags über die Zusammenarbeit auf dem Gebiet des Patentwesens (PCT) _____ und am _____ abgeändert (falls zutreffend).

Ich bestätige hiermit, daß ich den Inhalt der oben angegebenen Patentanmeldung, einschließlich der Ansprüche, die eventuell durch einen oben erwähnten Zusatzantrag abgeändert wurde, durchgesehen und verstanden habe.

Ich erkenne meine Pflicht zur Offenbarung jeglicher Informationen an, die zur Prüfung der Patentfähigkeit in Einklang mit Titel 37, Code of Federal Regulations, § 1.56 von Belang sind.

As a below named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated next to my name.

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled:

POLYMER-COATED THIN-GLASS FILM SUBSTRATES

the specification of which is attached hereto unless the following box is checked:

☒ was filed on April 17, 2000 as United States Application Number or PCT International Application Number PCT/EP00/03471 and was amended on _____ (if applicable).

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose information which is material to patentability as defined in Title 37, Code of Federal Regulations, § 1.56.

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

German Language Declaration

Ich beanspruche hiermit ausländische Prioritätsvorteile gemäß Title 35, US-Code, § 119 (a)-(d), bzw. § 365(b) aller unten aufgeführten Auslandsanmeldungen für Patente oder Erfindurkunden, oder §365(a) aller PCT internationalen Anmeldungen, welche wenigstens ein Land ausser den Vereinigten Staaten von Amerika benennen, und habe nachstehend durch ankreuzen sämtliche Auslands- anmeldungen für Patente bzw. Erfindurkunden oder PCT internationale Anmeldungen angegeben, deren Anmeldetag dem der Anmeldung, für welche Priorität beansprucht wird, vorangeht.

Prior Foreign Applications
(Frühere ausländische Anmeldungen)

99108440.1 Germany
(Number) (Country)
(Nummer) (Land)

(Number) (Country)
(Nummer) (Land)

Ich beanspruche hiermit Prioritätsvorteile unter Title 35, US-Code, § 119(e) aller US-Hilfsanmeldungen wie unten aufgezählt.

(Application No.) (Filing Date)
(Aktenzeichen) (Anmeldetag)

(Application No.) (Filing Date)
(Aktenzeichen) (Anmeldetag)

Ich beanspruche hiermit die mir unter Title 35, US-Code, § 120 zustehenden Vorteile aller unten aufgeführten US-Patentanmeldungen bzw. § 365(c) aller PCT internationalen Anmeldungen, welche die Vereinigten Staaten von Amerika benennen, und erkenne, insofern der Gegenstand eines jeden früheren Anspruchs dieser Patentanmeldung nicht in einer US-Patentanmeldung, bzw. PCT internationalen Anmeldung in in einer gemäß dem ersten Absatz von Title 35, US-Code, § 112 vorgeschriebenen Art und Weise offenbart wurde, meine Pflicht zur Offenbarung jeglicher Informationen an, die zur Prüfung der Patentfähigkeit in Einklang mit Title 37, Code of Federal Regulations, § 1.56 von Belang sind und die im Zeitraum zwischen dem Anmeldetag der früheren Patentanmeldung und dem nationalen oder im Rahmen des Vertrags über die Zusammenarbeit auf dem Gebiet des Patentwesens (PCT) gültigen internationalen Anmeldetags bekannt geworden sind.

EP00/03471 17 April 2000
(Application No.) (Filing Date)
(Aktenzeichen) (Anmeldetag)

(Application No.) (Filing Date)
(Aktenzeichen) (Anmeldetag)

Ich erkläre hiermit, daß alle in der vorliegenden Erklärung von mir gemachten Angaben nach bestem Wissen und Gewissen der Wahrheit entsprechen, und ferner daß ich diese eidesstattliche Erklärung in Kenntnis dessen ablege, daß wissentlich und vorsätzlich falsche Angaben oder dergleichen gemäß § 1001, Title 18 des US-Code strafbar sind und mit Geldstrafe und/oder Gefängnis bestraft werden können und daß derartige wissentlich und vorsätzlich falsche Angaben die Rechtswirksamkeit der vorliegenden Patentanmeldung oder eines aufgrund deren erteilten Patentes gefährden können.

I hereby claim foreign priority under Title 35, United States Code, §119(a)-(d) or § 365(b) of any foreign application(s) for patent or inventor's certificate, or § 365(a) of any PCT International application which designated at least one country other than the United States, listed below and have also identified below, by checking the box, any foreign application for patent or inventor's certificate, or PCT International application having a filing date before that of the application on which priority is claimed.

Priority Not Claimed
Priorität nicht beansprucht

30 April 1999
(Day/Month/Year Filed)
(Tag/Monat/Jahr der Anmeldung)

(Day/Month/Year Filed)
(Tag/Monat/Jahr der Anmeldung)

I hereby claim the benefit under Title 35, United States Code, § 119(e) of any United States provisional application(s) listed below.

I hereby claim the benefit under Title 35, United States Code, § 120 of any United States application(s), or § 365(c) of any PCT International application designating the United States, listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States or PCT International application in the manner provided by the first paragraph of Title 35, United States Code, § 112, I acknowledge the duty to disclose information which is material to patentability as defined in Title 37, Code of Federal Regulations, § 1.56 which became available between the filing date of the prior application and the national or PCT International filing date of this application.

Published
(Status) (patented, pending, abandoned)
(Status) (patentiert, schwebend, aufgegeben)

(Status) (patented, pending, abandoned)
(Status) (patentiert, schwebend, aufgegeben)

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

German Language Declaration

VERTRETUNGSVOLLMACHT: Als benannter Erfinder beauftrage ich hiermit den (die) nachstehend aufgeführten Patentanwalt (Patentanwälte) und/oder Vertreter mit der Verfolgung der vorliegenden Patentanmeldung sowie mit der Abwicklung aller damit verbundenen Angelegenheiten vor dem US-Patent- und Markenamt: (Name(n) und Registrationsnummer(n) auflisten)

POWER OF ATTORNEY: As a named inventor, I hereby appoint the following attorney(s) and/or agent(s) to prosecute this application and transact all business in the Patent and Trademark Office connected therewith: (list name and registration number)

John F. Hoffman, Regis. No. 26,280; Anthony Niewyk, Regis. No. 24,871; Michael D. Smith, Regis. No. 40,181; Michael S. Gzybowski, Regis. No. 32,816; Michael D. Schwartz, Regis. No. 44,326; Adam F. Cox, Regis. No. 46,644; Abigail M. Butler, Regis. No. P-48,738; Thomas A. Adams, Regis. No. P-48,230; and Kimberly J. Paulus, Regis. No. P-48,358; all of BAKER & DANIELS, 111 East Wayne Street, Suite 800, Fort Wayne, Indiana 46802, all of BAKER & DANIELS, 111 East Wayne Street, Suite 800, Fort Wayne, IN 46802.

Postanschrift:

Send Correspondence to:

Telefonische Ankünfte: (Name und Telefonnummer)

John F. Hoffman

Direct Telephone Calls to: (name and telephone number)

John F. Hoffman

(219) 424-8000

Vor- und Zuname des einzigen oder ersten Erfinders	1-00	Full name of sole or first inventor	Roland Bürkle
Unterschrift des Erfinders	Datum	Inventor's signature	Date
			Roland Bürkle 01/08/20
Wohnsitz		Residence	Nieder-Olm, Germany, Kirchentellinsfurt DEX
Staatsangehörigkeit		Citizenship	German
Postanschrift		Post Office Address	DR. ROLAND BÜRKLE PETER IMHUFF-STR. 51 D-55268 Nieder-Olm GERMANY
Vor- und Zuname des zweiten Miterfinders (falls zutreffend)	2-00	Full name of second joint inventor, if any	Silke Deutschbein
Unterschrift des zweiten Erfinders	Datum	Second Inventor's signature	Date
			Silke Deutschbein 24/10/2001
Wohnsitz		Residence	Mainz, Germany DEX
Staatsangehörigkeit		Citizenship	German
Postanschrift		Post Office Address	Wallaustrasse 79 D-55118 Mainz GERMANY

(Im Falle dritter und weiterer Miterfinder Miterfinder sind die entsprechenden Informationen und Unterschriften hinzuzufügen.)

(Supply similar information and signature for third and subsequent joint inventors.)

3-00
Reiner Mauch
Full Name of Third Inventor

[Signature]
Inventor's Signature

5.7.01
Date

Ingelheim, Germany

Residence

German

Citizenship

Kurpfalzstrasse 22

D-55218 Ingelheim, Germany

Post Office Address

4-00
Karl-Heinz Sossenheimer

Full Name of Fourth Inventor

[Signature]
Inventor's Signature

8.9.01
Date

Wackernheim, Germany

Residence

German

Citizenship

Auf der Unter 6

D-55263 Wackernheim, Germany

Post Office Address

5-00
Andreas Weber
Full Name of Fifth Inventor

[Signature]
Inventor's Signature

21.10.01
Date

Mainz, Germany

Residence

German

Citizenship

Max-Planck-Strasse 20

D-55124 Mainz, Germany

Post Office Address